



Dimension board	
LENGTH	1860 mm
WIDTH	189 mm
TOTAL THICKNESS	15.0 mm
THICKNESS TOP LAYER	4 mm
LAYER CONTENTS	Min 7 Pl x 1860

Dimension pack	
PACK LENGTH	1870 mm
PACK WIDTH	200 mm
PACK THICKNESS	130 mm
PACK WEIGHT	25 kg
LAYERS/BOX	8
M ² /PACK	2.81 m ²

Dimension pallet	
PALLET LENGTH	1890 mm
PALLET WIDTH	1000 mm
PALLET HEIGHT	1160 mm
PALLET WEIGHT	1000 kg
PACKS/PALLET	40
M ² /PALLET	112.40 m ²

CHARACTERISTICS

Ton	lavor
	laver

WOOD SPECIES	Oak
LATIN NAME	Quercus Mongolica
GRADE	CLASSIC
CONSTRUCTION	3-layer
THICKNESS TOP LAYER	4 mm
PATTERN	1 strip
CUTTING METHOD	Zaagfineer
BEVEL	Bevel 2 long sides 0,75 mm
FINISH	Oil
SURFACE STRUCTURE	Structured

Composition of the support

SUPPORT TYPE	Populier
WOOD SPECIES SUPPORT	Populier
TOTAL THICKNESS SUPPORT	11 mm
ADHESION	Kruiselings

Installation

SYSTEM	APPLICATIONS	UNDERFLOOR HEATING
Tongue and groove	Light household use.	Yes
	Moderate commercial use.	
	Normal commercial use.	RE-SANDABLE
	Normal household use.	Yes
	Intensive commercial use	

[©] This fact sheet was written by Labeco BVBA, Sprietestraat 326, B-8792 Waregem. Text, photographs, drawings, tables, graphs should in no way be distributed, used or copied unless LABECO BVBA has granted reproduction rights. At the moment of establishment of the sheet, all information is specified correctly. The company reserves the right to change the specifications of the product at any time without prior notice to third parties. The photographs, drawings, tables, graphs used in this sheet are intended only as illustrations. No rights can be derived from them.



TECHNICAL SPECIFICATIONS

	Norm	Result
REACTION TO FIRE	EN 13501-1	Dfl-S1
FORMALDEHYDE EMISSION	EN 717-1	E1
PCP	CEN/TR 14823	≤ 5ppm
THERMAL CONDUCTIVITY	EN 12667 / ISO 8302	0,11m² k/w
BIOLOGICAL DURABILITY	EN 335	Class 1
BREAKING STRENGTH	EN 1533	Pass
SLIPPERINESS	EN 15676	Pass
MOISTURE CONTENT	EN 13183-1	7% (+/-2%)

CERTIFICATION









