

# ABC - INVISIBLE OIL - BRUSHED A15328



Dimension	board
-----------	-------

LENGTH	2200 mm
WIDTH	190 mm
TOTAL THICKNESS	14.0 mm
THICKNESS TOP LAYER	3 mm
LAYER CONTENTS	Min 7 Pl x 2200 mm

### Dimension pack

PACK LENGTH	2210 mm
PACK WIDTH	195 mm
PACK THICKNESS	115 mm
PACK WEIGHT	20 kg
LAYERS/BOX	8
M <sup>2</sup> /PACK	2.51 m <sup>2</sup>

#### Dimension pallet

PALLET LENGTH	2210 mm
PALLET WIDTH	1000 mm
PALLET HEIGHT	1080 mm
PALLET WEIGHT	1060 kg
PACKS/PALLET	50
M <sup>2</sup> /PALLET	125.50 m <sup>2</sup>

## **CHARACTERISTICS**

Top layer

WOOD SPECIES	Oak
LATIN NAME	Quercus Robur
GRADE	ABC
CONSTRUCTION	3-layer
THICKNESS TOP LAYER	3 mm
PATTERN	1 strip
CUTTING METHOD	Zaagfineer
BEVEL	Bevel 2 long sides 0,75 mm
FINISH	Oil
SURFACE STRUCTURE	Brushed

# Composition of the support

SUPPORT TYPE	Populier
WOOD SPECIES SUPPORT	Populier
TOTAL THICKNESS SUPPORT	11 mm
ADHESION	Kruiselings

#### Installation

SYSTEM
APPLICATIONS
UNDERFLOOR HEATING

Yes

Moderate commercial use.
Normal commercial use.
Normal household use.
Yes

Intensive commercial use.

© This fact sheet was written by Labeco BVBA, Sprietestraat 326, B-8792 Waregem. Text, photographs, drawings, tables, graphs should in no way be distributed, used or copied unless LABECO BVBA has granted reproduction rights. At the moment of establishment of the sheet, all information is specified correctly. The company reserves the right to change the specifications of the product at any time without prior notice to third parties. The photographs, drawings, tables, graphs used in this sheet are intended only as illustrations. No rights can be derived from them.



# ABC - INVISIBLE OIL - BRUSHED A15328

## TECHNICAL SPECIFICATIONS

	Norm	Result
REACTION TO FIRE	EN 13501-1	Dfl-S1
FORMALDEHYDE EMISSION	EN 717-1	E1
PCP	CEN/TR 14823	≤5ppm
THERMAL CONDUCTIVITY	EN 12667 / ISO 8302	0,11m² k/w
BIOLOGICAL DURABILITY	EN 335	Class 1
BREAKING STRENGTH	EN 1533	Pass
SLIPPERINESS	EN 15676	Pass
MOISTURE CONTENT	EN 13183-1	7% (+/-2%)

## **CERTIFICATION**









