



**Size Board**

<b>LENGTH</b>	1900 mm
<b>WIDTH</b>	190 mm
<b>TOTAL THICKNESS</b>	14 mm
<b>THICKNESS TOP LAYER</b>	3 mm
<b>PLANK QUANTITY</b>	Min. 7 Pl. x 1900 mm

**Size Pack**

<b>PACK LENGTH</b>	1910 mm
<b>PACK WIDTH</b>	200 mm
<b>PACK THICKNESS</b>	120 mm
<b>PACK WEIGHT</b>	24 kg
<b>LAYERS/PACK</b>	8
<b>M<sup>2</sup>/PACK</b>	2.89 m <sup>2</sup>

**Size Pallet**

<b>LENGTH PALLET</b>	1930 mm
<b>WIDTH PALLET</b>	1000 mm
<b>HEIGHT PALLET</b>	1080 mm
<b>WEIGHT PALLET</b>	975 kg
<b>PACKS/PALLET</b>	40
<b>M<sup>2</sup>/PALLET</b>	115.6 m <sup>2</sup>

**Characteristics**

**Top layer**

<b>WOOD SPECIES</b>	Larch
<b>LATIN NAME</b>	Larix
<b>GRADE</b>	CLASSIC
<b>CONSTRUCTION</b>	3-layer
<b>THICKNESS TOP LAYER</b>	3 mm
<b>STRIPS</b>	1 strip
<b>CUTTING METHOD</b>	Sawn veneer
<b>BEVEL</b>	Two long sides (0,75 mm)
<b>COLOUR FINISH</b>	Brushed White oiled
<b>SURFACE STRUCTURE</b>	Brushed

**Composition of the support**

<b>SUPPORT TYPE</b>	Support and backing in Larch
<b>WOOD SPECIES SUPPORT</b>	Larch
<b>SUPPORT CONSTRUCTION</b>	2-layer (Support, balancer)
<b>TOTAL THICKNESS SUPPORT</b>	11 mm
<b>ADHESION</b>	Crosswise (Casco)

**Installation**

**SYSTEM**

Drop click system



**APPLICATIONS**

Light household use  
Moderate commercial use  
Normal commercial use  
Normal household use  
Intensive commercial use

**UNDERFLOOR HEATING**

Yes

**RESANDABLE**

Resandable

## Certification

This product conforms to CE standard EN 14342:2005 + A1: 2008 - Level 4 for flooring type BS EN 13489:2002 (Wood and parquet flooring, Multilayer parquet)

- Formaldehyde emission, determined according to standard EN 13183-1: E1
- Moisture content, determined according to standard EN 13183-1: 10% (+ / -2%). Fits in dry areas with a moisture content of 50% to 60%
- Width Shrinkage, complies with standard EN 13647
- Reaction to fire, determined according to standard EN 13501-1: Dfl-S1
- Does not contain any PCP (pentachlorophenol)

---

## Technical specifications

- Hardness: N / mm<sup>2</sup> (Birrell Hardness) 3.40
- Thermal conductivity:  $\lambda$  14, 00 (W / (mk)) R = 0.11 m<sup>2</sup> K / W

Additional tests:

- Tested for delamination and stability according to standard EN1910 (cf. 15-189-BRUT CLASSIC)
- The bonding was tested according to EN311 standard (see 15-189-BRUT CLASSIC)