



Size Board

| | |
|----------------------------|----------------------|
| LENGTH | 1900 mm |
| WIDTH | 150 mm |
| TOTAL THICKNESS | 12 mm |
| THICKNESS TOP LAYER | 3 mm |
| PLANK QUANTITY | Min. 7 Pl. x 1900 mm |

Size Pack

| | |
|---------------------------|---------------------|
| PACK LENGTH | 1910 mm |
| PACK WIDTH | 160 mm |
| PACK THICKNESS | 100 mm |
| PACK WEIGHT | 18 kg |
| LAYERS/PACK | 8 |
| M²/PACK | 2.28 m ² |

Size Pallet

| | |
|-----------------------------|-----------------------|
| LENGTH PALLET | 1930 mm |
| WIDTH PALLET | 1050 mm |
| HEIGHT PALLET | 1100 mm |
| WEIGHT PALLET | 1260 kg |
| PACKS/PALLET | 70 |
| M²/PALLET | 159.60 m ² |

Characteristics

Top layer

| | |
|----------------------------|--------------------------------------|
| WOOD SPECIES | Oak |
| LATIN NAME | Quercus |
| GRADE | CLASSIC |
| CONSTRUCTION | 2-layer |
| THICKNESS TOP LAYER | 3 mm |
| STRIPS | 1 strip |
| CUTTING METHOD | Sawn veneer |
| BEVEL | Micro bevel Two long sides (0,50 mm) |
| COLOUR FINISH | Brushed Invisible lacquer |
| SURFACE STRUCTURE | Brushed |

Composition of the support

| | |
|--------------------------------|----------------------|
| SUPPORT TYPE | Multiplex support |
| WOOD SPECIES SUPPORT | Mixed Light Hardwood |
| SUPPORT CONSTRUCTION | Multiplex (8 layers) |
| TOTAL THICKNESS SUPPORT | 9 mm |
| ADHESION | Crosswise (Casco) |

Installation

SYSTEM

Drop click system



APPLICATIONS

Light household use
Moderate commercial use
Normal commercial use
Normal household use
Intensive commercial use

UNDERFLOOR HEATING

Yes

RESANDABLE

Resandable

Certification

This product conforms to CE standard EN 14342:2005 + A1: 2008 - Level 4 for flooring type BS EN 13489:2002 (Wood and parquet flooring, Multilayer parquet)

- Formaldehyde emission, determined according to standard EN 13183-1: E1
- Moisture content, determined according to standard EN 13183-1: 10% (+ / -2%). Fits in dry areas with a moisture content of 50% to 60%
- Width Shrinkage, complies with standard EN 13647
- Reaction to fire, determined according to standard EN 13501-1: Dfl-S1
- Does not contain any PCP (pentachlorophenol)

Technical specifications

- Hardness: N / mm² (Birrell Hardness) 3.40
- Thermal conductivity: λ 14, 00 (W / (mk)) R = 0.11 m² K / W

Additional tests:

- Tested for delamination and stability according to standard EN1910 (cf. 15-189-BRUT CLASSIC)
- The bonding was tested according to EN311 standard (see 15-189-BRUT CLASSIC)