

15-CLASSIC-180-INV-BARN-DESIGN



Size **Board**

LENGTH	1260 mm
WIDTH	180 mm
TOTAL THICKNESS	15 mm
THICKNESS TOP LAYER	4 mm

Size **Pack**

PACK LENGTH	1270 mm
PACK WIDTH	190 mm
PACK THICKNESS	130 mm
PACK WEIGHT	19 kg
LAYERS/PACK	8
M²/PACK	1.81 m ²

Size **Pallet**

LENGTH PALLET	1290 mm
WIDTH PALLET	950 mm
HEIGHT PALLET	1160 mm
WEIGHT PALLET	775 kg
PACKS/PALLET	40
M ² /PALLET	72.4 m ²

Characteristics

Top layer


WOOD SPECIES	Oak
LATIN NAME	Quercus
GRADE	CLASSIC
CONSTRUCTION	2-layer
THICKNESS TOP LAYER	4 mm
STRIPS	90 x 90 mm
CUTTING METHOD	Axe split
BEVEL	No bevel
COLOUR FINISH	Invisible oiled
SURFACE STRUCTURE	Axe split

Composition of the support

SUPPORT TYPE	Multiplex support
WOOD SPECIES SUPPORT	Mixed Light Hardwood
SUPPORT CONSTRUCTION	Multiplex (7 layers)
TOTAL THICKNESS SUPPORT	11 mm
ADHESION	Crosswise (Casco)

Installation

Tongue and groove system Light household use Moderate commercial use Normal household use Not resandable Not resandable



15-CLASSIC-180-INV-BARN-DESIGN

Certification

This product conforms to CE standard EN 14342:2005 + A1: 2008 - Level 4 for flooring type BS EN 13489:2002 (Wood and parguet flooring, Multilayer parguet)

- Formaldehyde emission, determined according to standard EN 13183-1: E1
- Moisture content, determined according to standard EN 13183-1: 10% (+ / -2%). Fits in dry areas with a moisture content of 50% to 60%
- Width Shrinkage, complies with standard EN 13647
- Reaction to fire, determined according to standard EN 13501-1: Dfl-S1 $\,$
- Does not contain any PCP (pentachlorophenol)

Technical specifications

- Hardness: N / mm ² (Birnell Hardness) 3.40
- Thermal conductivity: λ 14, 00 (W / (mk)) R = 0.11 m² K / W

Additional tests:

- Tested for delamination and stability according to standard EN1910 (cf. 15-189-BRUT CLASSIC)
- The bonding was tested according to EN311 standard (see 15-189-BRUT CLASSIC)